

(MnFe₂O₄)
(8-12.5)GHz

(2008/5/26 2008/1/30)

ZnO Fe₂O₃ TiO₂)

. (MnFe₂O₄)

(MnO₂ Ni₂O₃ CdO CuO MgO

(8-12.5)GHz

SWR

(Ni₂O₃)

(MnO₂)

.

(87%)

(MnO₂)

.

(80.5%)

(Ni₂O₃)

(10.2-11.4)GHz

.

(10.8-12.4)GHz

**Preparation and Study Absorption Coatings from Two layers
Ferrite (MnFe₂O₄) and Different Metal Oxides within
Electromagnetic Frequency Bandwidth (8-12.5)GHz**

Ammar Y. Al-Jubory
Department of Physics
College of Science
Mosul University

ABSTRACT

Two layers coatings were prepared one of them is from different metal oxides (TiO₂, Fe₂O₃, ZnO, MgO, CuO, CdO, Ni₂O₃, MnO₂) and the other is from ferrite powder

(MnFe_2O_4) for each sample. Absorption measurements for electromagnetic (EM) waves in the frequency range (8-12.5)GHz were achieved by the standing wave ratio SWR instrument. In addition a study of the effect in exchanging the oxide layer with the ferrite powder layer when they are radiated by (EM) waves. It was noticed that the oxide layer (MnO_2) and the oxide layer (Ni_2O_3) were the best among other prepared samples as they posses nearly equal absorption values with the ferrite layer when they are subjected to the (EM) waves directly and in exchange with the ferrite layer. The (MnO_2) oxide with the ferrite showed an absorption value of (87%) at the frequency range (10.2-11.4)GHz, while the (Ni_2O_3) oxide with the ferrite showed an absorption value of (80.5%) at the frequency range (10.8-12.4)GHz in comparison with other prepared samples.

(M) (MFe_2O_4)
(
Hatakeyama, Inui .(Grimes *et al.*, 1976)
(resin)
.
(Hatakeyama and Inui, 1985)
X-band (1999)
($\text{MnZnFe}_2\text{O}_4$)
(98%) (10.5GHz)
Peterman .(2-3.1)mm
(
)
(rotating retort) (
(SiH , SiF_4 , SiCl_4)
(2002) .(Peterman, 2002)

.....

(Fe₃O₄) (8-12.5)GHz
(2-3)mm
(2003) .(75%)
X
.
(11%) (21%)
(2004)
(10GHz)
(73.12%)
(MnFe₂O₄) (2007) .(2.1)mm
. X

(9-10)GHz (106.5-500) μ m
(9.5-11)GHz (200-780) μ m

(8-12.5)GHz

.

RAM

.

SWR

R

:

$$R=[Z\tanh(\gamma d)-Z_o / Z\tanh(\gamma d)+Z_o]$$
(1)

$$\gamma \qquad d \qquad Z_o \qquad Z$$

(1)

$$Z_o = Z \tanh(\gamma d) \dots\dots\dots(2)$$

(2.1)mm

.(Vinoy and Jha, 1996) (35)dB

.(Dixon, 2004)

:

.1

.(1977)

Hysteresis

.(1985)

.2

.(1985)

(1986)

.....

:(Connor,1972)

(Lance,1964)

$$SWR = \left| V_{\max} \right| / \left| V_{\min} \right| \dots\dots\dots(3)$$

$$V_{\min} \qquad \qquad \qquad V_{\max} \qquad \qquad \qquad SWR$$

:(1)

$$SWR = \left| V_{\max} \right| \dots\dots\dots(4)$$

:(Connor,1972)

ρ

$$\left| \rho \right| = (SWR-1) / (SWR+1) \dots\dots\dots(5)$$

:(2002)

$$\rho + T + \alpha = 1 \dots\dots\dots(6)$$

= T

α

T

()

:

α

$$\alpha = (1- \rho) \dots\dots\dots(7)$$

:

$$Absorption(A\%)=\alpha *100 \% \dots\dots\dots(8)$$

:

:

(MnFe₂O₄)

.1

MgO

ZnO

Fe₂O₃

TiO₂

MnO₂

Ni₂O₃

CdO

CuO

. Garantie-Fluka

(99.9%)


.

(8x8)cm .2

.3

SWR .4

:(1)



:1

:

:

(1.5gm)

(1.5gm)

(5x5)cm

(1.5gm)

.(1.14mm)

(1.5gm)

(MnO₂ Ni₂O₃ CdO CuO MgO ZnO Fe₂O₃ TiO₂)

(2gm)

(2gm)

CuO=1.12mm MgO=1.46mm ZnO=1.4mm Fe₂O₃=1.31mm TiO₂=1.37mm)

(5x5)cm


(MnO₂=1.27mm Ni₂O₃=1.28mm CdO=1.29mm

(2)

(1)

()

.(2)



:2

1

TiO₂

(1)

(2)

•

•

.2

()

(8GHz)

SWR ($V_{\max}=\infty$)

SWR

SWR

 $(V_{\min}=1)$

SWR

■

VSWR .3

()

 $(V_{\min}=1)$


(8)GHz

()


SWR

SWR $(V_{\max})$
 (8.2,.....12.4)GHz .SWR
 (0.2)GHz
 (1) (2)
 (2) (1)
 VSWR

(Ni_2O_3 , MnO_2 , CdO , CuO , MgO , ZnO , Fe_2O_3)
 (10,9,8,7,6,5,4,3)
 . (8-3) VSWR




:3
 (2.51mm) Ferrite+ TiO_2



:4

(2.45mm)


Ferrite+Fe₂O₃



:5

(2.54mm)


Ferrite+ZnO



:6

(2.6mm)

Ferrite+MgO




:7

(2.26mm)

Ferrite+CuO


.....



:8

(2.43mm)


Ferrite+CdO



:9

(2.41mm)

Ferrite+MnO₂



:10

(2.42mm)

Ferrite+Ni₂O₃

GHz

(A%)

(3)

(2.51mm)

(9-12.2)GHz

(80.5%)

.TiO₂

(4)

(2.45mm)

(81.6%)

.Fe₂O₃

(10.2-12.4)GHz

(5)

ZnO

(2.54mm)

(10.2-12.0)GHz

(84.5%)

.....

(6)

(2.60mm)

(9.8-12.4)GHz

(86%)

.MgO

(7)

(2.26mm)

(83%)

CuO

.(10.2-12.2)GHz

(8)

(2.43mm)

(10.2-12.0)GHz

(83%)

.CdO

(MnO₂)

(9)

(87%)

(2.41mm)

(10.2-11.4)GHz

.

(10)

(2.42mm)

(Ni₂O₃)

(80.5%)

(10.8-12.4)GHz

.

Hysteresis Loss

(Ni₂O₃,MnO₂)

(2001)

)

	(1989) (X>>1)	(	
.(Grimes <i>et al.</i> , 1976) (ϵ)	(μ)		
VSWR	(8-12.5)GHz		
	:	(0.2GHz)	
(70%)			.1
	(8.6 - 12)GHz		
TiO ₂			.2
	(8 - 9.4)GHz		
	(9.6-12)GHz		
	(CdO CuO MgO Fe ₂ O ₃)		
CuO MgO TiO ₂ Fe ₂ O ₃)			.3
	(CdO		
ZnO			.4
	(10.2-12)GHz	(85%)	
	(MnO ₂)		.5
.(87%)	(10.2-11.4)GHz)		
(Ni ₂ O ₃)	(10.8-12.4)GHz		.6
	(80%)		
			.7
(10GHz)	(2004) (1999)		.8
.(X)			

.....

(2007) (9.5-12)GHz .9

(9.5-11)GHz

(MnFe₂O₄)

.(X) (2002) .10

.11

.2003

X

.1985

10GHz

.2004

.2002

.1986

.1977

.2001

.1999

.2007

X

.1989

- Dixon, P., 2004. Damping Cavity Resonance Using Absorber Material. Microwave Technology, pp.16-19.
- Connor, F.R., 1972. Wave Transmission. Edward Arnold, London,p31.
- Grimes, D.M.; Raymond, W.W.; Hach, R.J., and Walser, R.M., 1976. Magnetic Absorbers, United State Patent No. 3, 938, 152p.
- Hatakeyyama, K., and Inui, T., 1985. Electro–Magnetic Wave Absorbing Material. United State Patent No. 4, 538, 151p.
- Lance, A.L., 1964. Introduction to Microwave Theory and Measurements. Mc Graw – Hill, USA,p25.
- Peterman, D., 2002. Chemically Modified Radar Absorbing Materials and Associated Fabrication Method. United State Patent No. 6, 486, 822p.
- Seeger, J.A., 1986. Microwave Theory, Component's and Devices. Prentice –Hall, New Jersey.
- Vinoy, K.J., and Jha, R.M., 1996. Radar Absorbing Materials, from Theory to Design and Characterization. Kluwer Academic Publishers, Boston, Dordrecht, London.